

**Backfill**  
**Gypsum Bentonite (anodes)**



Savcor Products supply backfill for buried magnesium and zinc galvanic anodes.

Anodes can be supplied in a complete package with backfill and anode inside calico bag with cable upon request.

Backfill supplied meets standard AS 2239 – 2003.

Savcor Products supply backfill for buried magnesium and zinc galvanic anodes.

Anodes can be supplied in a complete package with backfill and anode inside calico bag with cable upon request.

Backfill supplied meets standard AS 2239 – 2003.

1. *Packaged anode*
2. *Cut away of packaged anode*

**Typical Properties:**

*Savcor Standard Backfill (B1)*

Composition: Calcium Bentonite 50% /Gypsum 50%

Resistivity when wet: Typically 3-6Ω.m

Water retention: Good.

Moisture: Max 18.00 Test Method 1009

Sieve: 100% Passing 0.6mm Test Method 1015

Min 70% Passing 0.15mm

pH 5% solids 7.0 to 10.0 Test Method 1018

Appearance: Fine Lgt Grey

Approx density 0.8kg/lt

Type B2 and B3 available on request.

**Application:**

Anode shall be covered with backfill not less than 50mm over each surface in a tightly fitting calico bag.

Vic/Tas/SA 03 9993 7500	NSW 02 9663 2322	NZ 09 414 5080	QLD/NT 07 3890 8533	WA 08 9248 8999
----------------------------	---------------------	-------------------	------------------------	--------------------

All written data and statements herein are provided in good faith and believed to be reliable and appropriate at the time of drafting this document. However it is given without implied or express guarantee. Potential uses are urged to trial and /or conduct conformity test of the product to deem its suitable in application for a particular end use prior to purchase.